

## Technical Data Sheet

Product Number S2-8575-5  
 Product Name HELIOCOLOR-W BLACK 7  
 Color-Index PBK 7

Issue Date 25.07.2023

### Composition

Pigment content [%] 20,000  
 solid content [%] 97,220  
 plasticiser [%] 78,000

### Specification

#### EP12

Specification	min. Level	max. Level	Plan Level	Text	Test method
Standard lot no.				F150847	
STD-BATCH delta L	-0,8000	0,8000			PM-0020
STD-BATCH delta a	-0,8000	0,8000			PM-0020
STD-BATCH delta b	-0,8000	0,8000			PM-0020
STD-BATCH delta E		1,0000			PM-0020
STD-BATCH delta CS	97,5000	102,5000			PM-0020
Fineness of grain [µm]		20,0			PM-0012
Density [kg/L]	0,993	1,055	1,024		PM-0019
Viscosity m/Pas [mPas]	1.000	6.000			PM-0080

### Fastnesses of the basic pigments in the pigment preparation

Lightfastness (Full shade / Reduction) 8 / 8  
 Wether Fastness (Full shade / Reduction) 5 / 5  
 Alkali Resistance 5  
 Acid Resistance 5  
 Temperature Resistance [°C] 250

### Tariff of duties no.

32129000

### Origin of goods

Germany

### Inventory

EC-No Yes  
 Schweiz (EC-No/EINECS) Yes  
 TSCA-USA Yes  
 AICS-Australien Yes  
 DSL/NDSL-Kanada Yes  
 PICCS-Philippinen Yes  
 MITI/ENCS-Japan Yes  
 ECL-Korea Yes  
 TCSI-Taiwan Yes  
 NZIOC-New Zealand Yes  
 IECSC-China Yes

## Technical Data Sheet

Product Number	S2-8575-5
Product Name	HELIOCOLOR-W BLACK 7
Color-Index	PBK 7

Issue Date	25.07.2023
------------	------------

### Important Notice

Always test the preparation for compatibility and suitability in the intended application system.

Suitable pigments should be specifically selected for each application system.

Colour index data refers to the basic pigment form.

Values provided on this data sheet are typical and may vary as the products are standardised according to colour strength.

The data provided herein is based on our current knowledge but does not guarantee any particular property.

It is the responsibility of the end user to ensure that products utilising these materials meet and comply with all relevant laws and regulations.

Stir well before use!

Close the container after use!